

Exceed™ performance polymers for new value-added extrusion coating and lamination solutions



Extrusion coating and lamination on various substrates such as board, paper, flexible films and HDPE woven fabrics, impart properties that prove beneficial for diverse end use applications. Extrusion coating and lamination also contribute towards decreasing the permeability of liquids, improved adhesion strength, sealing and toughness. Traditionally, LDPE and butene based LLDPE copolymers have been used as the material of choice.

ExxonMobil introduces Exceed™ 0015XC and Exceed 0019XC performance polymers based solutions for extrusion coating and lamination, delivering enhanced toughness and sealing performance. Further, ExxonMobil's robust supply chain ensures consistent supply of these resins in various regions globally.

LDPE supply shortfall

In 2020, LDPE demand in India was estimated at 889kt & forecasted to grow at 4.6% CAGR (Compound Annual Growth Rate) for the next 5 years until 2025. With current domestic manufacturing capacity for LDPE slated at 605kt & no new capacity additions anticipated the dependence on global suppliers is bound to increase. Further pace of new capacity additions in global production of LDPE is estimated at 3.3%, much lower than growth forecasted for LDPE demand in India. (Source: Townsend 2019 PE report)

Exceed performance polymers

Exceed performance polymers are ethylene 1-hexene copolymers designed to deliver superior mechanical and sealing performance for highly demanding end-use applications, compared to conventional LDPE & LLDPE resins. Two resins in the portfolio, Exceed 0015XC and Exceed 0019XC, that are new to the Indian market are tailor-made for extrusion coating and lamination on

different substrates like board, paper, flexible films and HDPE woven fabrics. They offer the following benefits:

- Outstanding sealing properties, especially lower sealing temperature
- Broad hot tack window
- Improved adhesion strength at lower melt temperature
- Opportunities to downgauge the coating thickness
- Easy processability with minimum blending of LDPE
- Good organoleptics
- Global availability

Compared to conventional LDPE & LLDPE, using Exceed performance polymers provides superior performance for better product integrity and less failure-in-use, while helping ease the pressure caused by LDPE shortages and price variations.



Pond liner



Paper cup coating



Tarpaulin

Performance tests


Exceed™ 0015XC and Exceed 0019XC are dedicated for extrusion coating and lamination processes. The table below lists the ExxonMobil PE polymers commonly used in the extrusion coating and lamination process.

Resin	MI (g/10 min)*	Density (g/cc)*
Exceed™ 0015XC	15	0.918
Exceed™ 0019XC	19	0.918
LDPE LD258	8.2	0.919
LDPE LD259	12	0.915

*Data from tests performed by or on behalf of ExxonMobil

The rheological behavior (see Figure 1) of Exceed 0015XC and Exceed 0019XC performance polymers helps make them easy to process. Offering increased draw down, these polymers allow line speeds to be increased, while maintaining product quality and consistency. These polymers also offer coating possibilities for weights as low as 5 gsm with line speeds varying from 50 m/min to 300 m/min. Exceed 0019XC is the preferred resin for lower coating thickness at higher line speeds. Exceed 0015XC and Exceed 0019XC can create opportunities for downgauging which translates into potential cost savings, while delivering superior performance. It is recommended that these resins are used with a blend of up to 30% LDPE 258/259 or any equivalent LDPE to control the neck-in.


Figure 1: Viscosity curve at 190°C**



**Data from tests performed by or on behalf of ExxonMobil

Figure 2 shows that Exceed 0015XC blended with LDPE delivers lower neck-in. Exceed 0019XC blended with LDPE allows lower motor load and back pressure.

Figure 2: Process-ability at 320°C***




Polymers tested in mono extrusion coating, on a 3.5 inch extruder designed for the extrusion coating process, at 320°C set temperature.

Reference	80% Exceed™ 0015XC ExxonMobil™ LDPE LD258	80% Exceed™ 0015XC performance polymer 20% ExxonMobil™ LDPE LD259	80% Exceed™ 0019XC performance polymer 20% ExxonMobil™ LDPE LD258	80% Exceed™ 0019XC performance polymer 20% ExxonMobil™ LDPE LD259
-----------	--	--	--	--

*** Data from tests performed by or on behalf of ExxonMobil

As can be seen in Figure 3, Exceed™ Performance PE rich blends outperform LDPE in sealing and mechanical performance. The spider chart represents the properties of a mono extrusion coating on 70 gsm kraft paper under standard conditions, with a line speed of 100 m/min and a set temperature of 320°C (608°F). The reference polymer is LD258 or other equivalent LDPE resins commonly used in the market. With a higher seal strength and broad hot tack plateau contributing to a broad operating window, Exceed 0015XC and Exceed 0019XC are outstanding sealants. In terms of tear and flex crack resistance, they also outperform the reference resins.

Figure 3: Sealing and mechanical performance***



Structures produced on EM pilot extrusion coating line
25 gsm polymer coated onto 70 gsm Kraft paper at
320°C set temp.

Reference

100% ExxonMobil™
LDPE LD258

Solution 1

80% Exceed™ 0015XC
performance polymer
20% ExxonMobil™M
LDPE LD259

Solution 2

80% Exceed™ 0019XC
performance polymer
20% ExxonMobil™M
LDPE LD259

*** Data from tests performed by or on behalf of ExxonMobil

For more information, kindly contact our regional representatives:

Jigar Palicha

PE Customer and Application Development Lead
Indian Subcontinent
jjigar.palicha@exxonmobil.com

Jatin Ashara

Market Development Manager
Indian Subcontinent
jatinkumar.b.ashara@exxonmobil.com

About ExxonMobil product solutions:

ExxonMobil Product Solutions is one of the largest chemical manufacturers in the world. Our unique portfolio of commodity and specialty businesses generates annual sales of nearly 25 million tons of prime products.

About ExxonMobil polyethylene:

With products that deliver critical properties such as strength, durability and toughness, easier sealability, and outstanding optics, our leading-edge polyethylene formulations help create, protect and promote products throughout the packaging, agriculture, industrial, personal care and hygiene markets. From store shelves, to harvesting, to shipping, to the factory, our products help reduce risk of waste, breakage and spoilage across the value chain.



©2022 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

Contact us for more information:
www.exxonmobilchemical.com/PE

ExxonMobil