



Exceed™ XP Enable™

**ExxonMobil**

Energy lives here™



## Help brand owners protect their food products using extreme performance packaging

Exceed™ XP performance polymers offer a new benchmark for a variety of high integrity food packaging applications that require extreme performance. This portfolio of products enables converters to cost-effectively fabricate extremely damage-resistant film to protect and preserve food products with high integrity packaging — from production to consumption.



Extreme toughness  
and flex-crack  
resistance



Enhanced  
stiffness



Excellent seal  
performance



High melt  
strength

### High package integrity

The Exceed XP family of performance products provides a number of options for enhanced flexible food packaging solutions. Exceed XP enables converters to fabricate films that deliver excellent performance: exceptional toughness, very high dart impact, aged property retention and sealability (including low seal initiation temperature and broad hot-tack range). Films made with these polymers offer extreme performance for flexible food packaging, including pouches and bags, that needs to withstand demanding environment, like freezers, or be capable of holding large quantities or heavy contents. This includes frozen food, dry food and meat and cheese applications.

### Innovation opportunities

Sharing knowledge and working together to harness collective expertise across the value chain helps us create differentiated solutions. The melt strength and toughness of Exceed XP allows the fabrication of films with extreme performance or to reduce film thickness, while maintaining performance. Films

made with Exceed XP do not require traditional melt strength enhancers which may deteriorate the desired performance properties of the film. This creates opportunities for converters to enhance the performance of their structures, while also providing possibilities for downgauging. Exceed XP is also well suited for use on mono-layer lines, providing performance on a wide variety of extrusion configurations.


### Cost optimization

Exceed XP performance polymers allow converters to increase output and optimize film formulations. These polymer grades offer a range of options for high melt strength and ease of extrusion to optimize solutions and deliver opportunities for high output.


The extreme toughness combined with the melt strength allows converters to tailor film solutions through linear polyethylene blends or downgauging. The high versatility of these Exceed XP grades, in terms of performance and processing capabilities, allows converters to simplify their inventories which can lower costs.

**Figure 1:**

Selected film property data for Exceed XP formulated films and the reference film.

**Figure 2:**

Selected film property data for Exceed XP formulated film and the reference film.

**Table 1: Product data for Exceed XP formulated films and the reference film.**

	Melt index (g/10 min)	Density (g/cm <sup>3</sup> )	Exceed XP coextruded 3-layer 40 μm film	Reference coextruded 3-layer 40 μm film	Reference coextruded 3-layer 40 μm film
Exceed XP 8656	0.5	0.916	●	●	
HDPE	0.7	0.961	●	●	●
C4LLDPE	1	0.918		●	
C8LLDPE	1	0.916			●
LDPE	0.75	0.923			●

**Table 2: Product data for Exceed XP formulated film and the reference film.**

	Melt index (g/10 min)	Density (g/cm <sup>3</sup> )	Exceed XP coextruded 3-layer 50 μm film	Reference coextruded 3-layer 50 μm film
Exceed XP 6056	0.5	0.916	●	
C8LLDPE	1	0.916	●	●
2 MI LDPE	2	-	●	●
C8mLLDPE	-	-		●

## Exceed™ 2012 performance polymer

Exceed 2012 performance PE polymer delivers flexible food and liquid packaging films with excellent sealing performance and outstanding extrudability and enables converters to fabricate films that deliver excellent performance: exceptional toughness, very high dart impact and sealability including low seal initiation.

Grades	Melt index (g/10 min)	Density (g/cm <sup>3</sup> )	Melt flow ratio (I <sub>21</sub> /I <sub>2</sub> )	Slip/anti-block	Distinguishing features for eXtreme Performance
Exceed XP 8784ML	0.8	0.914	28-32	No	Easy extrusion and good bubble stability, step-out mechanical performance, excellent sealing performance
Exceed XP 8656ML	0.5	0.916	28-30	No	Extreme toughness, exceptional flex-crack resistance with high melt strength
Exceed XP 8358ML	0.5	0.918	28-30	No	Extreme toughness, high flex-crack resistance with enhanced stiffness
Exceed XP 8318ML	1.0	0.918	28-30	No	Extreme toughness with enhanced ability to extrude
Exceed XP 6056ML	0.5	0.916	36-38	No	Excellent balance of melt strength, toughness, sealing and ability to extrude
Exceed XP 6026ML	0.2	0.916	48-52	No	Extreme melt strength and toughness combined for lamination and thicker films
Exceed 2012MA	2.0	0.912	-	No	Excellent sealing performance and extrudability

<sup>1</sup> Tris(nonylphenyl)phosphite (TNPP) CAS# 26523-78-4 is not intentionally used by ExxonMobil in this product. Although this product is not routinely tested for its presence, based on product composition knowledge this substance is not expected to be present. However, the fact that this substance is not intentionally used by ExxonMobil in this product does not exclude that trace levels of this substance may be present as a result of the specific characteristics of the raw materials and/or of the manufacturing process.

Food contact compliance: Please contact ExxonMobil Chemical Customer Service for the official food law certificates which provide more detailed information.

**Exceed™ XP performance polymers — when eXtreme Performance matters.**

### Test methods based on

ASTM D-1238	ASTM D-882	ExxonMobil test method
ASTM D-4703	ASTL D-1709	
ASTM D-1505 / ISO 1183	ASTM D-5748	
ASTM D-1746	ASTM F-1921	
ASTM D-1003	ASTM F-2029	
ASTM D-2547	CEN 14477	



©2019 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

Contact us for more information:  
[exxonmobilchemical.com/pe](http://exxonmobilchemical.com/pe)

**ExxonMobil**

Energy lives here™