

# Polypropylene product finder

Energy lives here

	MFR (230°C, 2.16kg) (g/10min) ASTM D1238	Flexural modulus 1% secant (kpsi) at 0.051 in/min ASTM D790A	Notched Izod impact (ft-lb/in) at 73°F ASTM D256A	Deflection temperature under load (DTUL) at 66 psi - Unannealed (°F) ASTM D648	Automotive	Appliance	Nonwoven	Rigid packaging	Flexible packaging	Consumer
<b>Achieve™ Advanced PP</b>	Typical values				Applications					
Achieve Advanced PP6282NE2	1.8	300	0.88	248				●		●
Achieve Advanced PP6302E1	1.9	296	0.88	253	●			●		
Achieve Advanced PP7123KNE1	11	228	1.6	241		●		●		
Achieve Advanced PP3854	24	--	--	--			●			
Achieve Advanced PP8285E1	30	144	No break	198	●					●
Achieve Advanced PP1605	32	196	0.49	200			●			●
Achieve Advanced PP6035G1	500	--	--	--			●			
Achieve Advanced PP6936G2	1550	--	--	--	●		●			
<b>ExxonMobil™ PP</b>	Typical values				Applications					
ExxonMobil PP5341E1	0.83	206	0.95	195	●					
ExxonMobil PP4052E1	2.0	248	0.80	207					●	
ExxonMobil PP5262	2.0	242	0.81	235				●		
ExxonMobil PP1572	2.1	298	1.2	233				●		
ExxonMobil PP9122	2.1	141	1.3	179	●			●		
ExxonMobil PP4792E1	2.7	212	0.92	191					●	
ExxonMobil PP4712E1	2.8	211	0.66	198					●	
ExxonMobil PP4912E1	2.8	240	0.68	211					●	
ExxonMobil PP6262	2.8	258	0.78	226				●		
ExxonMobil PP6272NE1	2.8	246	1.2	230				●		
ExxonMobil PP2252E1	3.5	--	--	--						●

# North America

	MFR (230°C, 2.16kg) (g/10min) ASTM D1238	Flexural modulus 1% secant (kpsi) at 0.051 in/min ASTM D790A	Notched Izod impact (ft-lb/in) at 73°F ASTM D256A	Deflection temperature under load (DTUL) at 66 psi - Unannealed (°F) ASTM D648	Automotive	Appliance	Nonwoven	Rigid packaging	Flexible packaging	Consumer
ExxonMobil PP7032E2	4.0	164	--	180	●			●		
ExxonMobil PP7032KN	4.0	201	No break	223		●		●		●
ExxonMobil PP2252E4	4.2	--	--	--						●
ExxonMobil PP1352E1	5.5	224	0.66	200		●				●
ExxonMobil PP9513	7.3	130	0.96	162					●	
ExxonMobil PP7033E2	8.0	153	3.1	176	●					●
ExxonMobil PP7033N	8.0	197	4.0	212	●	●		●		●
ExxonMobil PP7143KNE1	10	164	No break	203				●		●
ExxonMobil PP9054	12	177	0.62	181						
ExxonMobil PP9574E6	12	144	1.6	169				●		
ExxonMobil PP1024E4	13	198	0.51	195	●			●		●
ExxonMobil PP8244E1	16	136	No Break	189	●					
ExxonMobil PP7654KNE2	17	179	4.4	206	●					●
ExxonMobil PP7684KNE1	19	185	3.0	221				●		●
ExxonMobil PP7694E2	19	189	3.2	212		●				●
ExxonMobil PP1264E1	20	187	0.50	201		●				●
ExxonMobil PP1074KNE1	20	262	0.59	248				●		●
ExxonMobil PP7414	20	150	3.3	185	●	●				●
ExxonMobil PP9074MED	24	153	1.2	167						●
ExxonMobil PP7855E1	30	160	3.2	202	●	●				●
ExxonMobil PP8255E1	30	173	3.6	205	●	●				
ExxonMobil AXO3BE3	35	203	1.4	226	●	●				●
ExxonMobil PP1105E1	35	205	0.49	202	●			●		●
ExxonMobil PP7035E4	35	146	2.9	175				●		●
ExxonMobil PP7035E5	35	152	2.7	192				●		●
ExxonMobil PP7815E1	35	266	1.3	--	●					
ExxonMobil PP3155E5	36	--	--	--			●			●
ExxonMobil PP7505KNE3	50	152	2.2	205	●			●		●
ExxonMobil PP7905E1	100	272	0.66	256	●					

©2019 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.