

Solvesso™ 200

Aromatic Fluid

Product Description

High solvency C11 aromatic fluid, suitable for:
 Agricultural chemicals
 Coatings
 Fuel Additives
 Foundry resin
 Oilfield and refinery chemicals

General

Specification Region	Latin America	North America
----------------------	---------------	---------------

Properties	Minimum	Maximum	Unit	Test Method
Appearance	Pass	--		Visual
Aromatic Content	98	--	wt%	GC1
Color, ASTM	--	1.0		ASTM D1500 ASTM D6045
Flash Point	95	--	°C	ASTM D93
Specific Gravity (15.6/15.6°C)	0.980	1.010		ASTM D4052

Distillation	Minimum	Maximum	Unit	Test Method
Distillation Range				ASTM D86
Initial Boiling Point (IBP)	220	--	°C	
Final Boiling Point (FBP)	--	290	°C	

Notes

ExxonMobil's sampling and testing procedures in effect at the time of production will be used for certification testing. Results may be based on tank certification, manufacturing data, periodic testing and/or most recent product restock. ExxonMobil reserves the right to use other equivalent test methods in certifying this product.

This product contains approximately 25 ppm BHT as added to the manufacturing site certified storage tank

The test methods specified above, or their equivalent, will be used in conjunction with ASTM D3244, "Standard Practices for Utilization of Test Data to Determine Conformance with Specifications."

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com