

# Santoprene™ 291-75B150

## Thermoplastic Vulcanizate

### Product Description

A colorable, specialty thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. It is especially formulated to bond to PC, ABS, PC/ABS, ASA and PMMA for applications where hard/soft combinations are required. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding or extrusion. It is recyclable within the manufacturing stream.

### Key Features

- Designed for excellent adhesion to PC, ABS, PC/ABS, ASA and PMMA (cold insert or 2K [two-shot] molding).
- Broad processing window in injection molding.
- Recommended for applications requiring superior part surface appearance.
- UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component.

### General

Availability <sup>1</sup>	<ul style="list-style-type: none"> <li>▪ Africa &amp; Middle East</li> <li>▪ Asia Pacific</li> </ul>	<ul style="list-style-type: none"> <li>▪ Europe</li> <li>▪ Latin America</li> </ul>	<ul style="list-style-type: none"> <li>▪ North America</li> </ul>
Applications	<ul style="list-style-type: none"> <li>▪ Automotive - Plugs, Bumpers, Grommets, Clips</li> <li>▪ Consumer - Floor Care</li> <li>▪ Consumer - Kitchen Tools</li> </ul>	<ul style="list-style-type: none"> <li>▪ Consumer - Power Tools</li> <li>▪ Consumer - Writing Instruments</li> <li>▪ Consumer Applications</li> </ul>	<ul style="list-style-type: none"> <li>▪ Seals and Gaskets</li> <li>▪ Soft Touch Grips</li> </ul>
Uses	<ul style="list-style-type: none"> <li>▪ Appliance Components</li> <li>▪ Appliances</li> <li>▪ Automotive Applications</li> <li>▪ Automotive Under the Hood</li> <li>▪ Bonding</li> <li>▪ Cell Phones</li> </ul>	<ul style="list-style-type: none"> <li>▪ Consumer Applications</li> <li>▪ Eyeglass Frames</li> <li>▪ Flexible Grips</li> <li>▪ Kitchenware</li> <li>▪ Living Hinges</li> <li>▪ Seals</li> </ul>	<ul style="list-style-type: none"> <li>▪ Sporting Goods</li> <li>▪ Strain Reliefs</li> <li>▪ Tie-Layer</li> <li>▪ White Goods &amp; Small Appliances</li> </ul>
Agency Ratings	<ul style="list-style-type: none"> <li>▪ UL QMFZ2</li> </ul>	<ul style="list-style-type: none"> <li>▪ UL QMFZ8</li> </ul>	
RoHS Compliance	<ul style="list-style-type: none"> <li>▪ RoHS Compliant</li> </ul>		
UL File Number	<ul style="list-style-type: none"> <li>▪ E80017</li> </ul>		
Color	<ul style="list-style-type: none"> <li>▪ Natural Color</li> </ul>		
Form(s)	<ul style="list-style-type: none"> <li>▪ Pellets</li> </ul>		
Processing Method	<ul style="list-style-type: none"> <li>▪ Coextrusion</li> </ul>	<ul style="list-style-type: none"> <li>▪ Injection Molding</li> </ul>	<ul style="list-style-type: none"> <li>▪ Multi Injection Molding</li> </ul>
Revision Date	<ul style="list-style-type: none"> <li>▪ 06/20/2014</li> </ul>		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	1.10	1.10	ASTM D792
Density	1.10 g/cm <sup>3</sup>	1.10 g/cm <sup>3</sup>	ISO 1183

  

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Shore Hardness Shore A, 15 sec, 73°F (23°C)	74	74	ISO 868

## Santoprene™ 291-75B150

Thermoplastic Vulcanizate

Elastomers	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100% - Across Flow (73°F (23°C))	464 psi	3.20 MPa	ASTM D412
Tensile Stress at 100% - Across Flow (73°F (23°C))	464 psi	3.20 MPa	ISO 37
Tensile Strength at Break - Across Flow (73°F (23°C))	2230 psi	15.4 MPa	ASTM D412
Tensile Stress at Break - Across Flow (73°F (23°C))	2230 psi	15.4 MPa	ISO 37
Elongation at Break - Across Flow (73°F (23°C))	640 %	640 %	ASTM D412
Tensile Strain at Break - Across Flow (73°F (23°C))	640 %	640 %	ISO 37
Compression Set			ASTM D395B
73°F (23°C), 22 hr, Type 1	37 %	37 %	
158°F (70°C), 22 hr, Type 1	68 %	68 %	
Compression Set			ISO 815
73°F (23°C), 22 hr, Type A	37 %	37 %	
158°F (70°C), 22 hr, Type A	68 %	68 %	

### Injection Notes

Santoprene TPV is incompatible with acetal and PVC. Please see Quick Processing Reference for 291-XXB150 for further information.

Aging	Typical Value (English)	Typical Value (SI)	Test Based On
Change in Tensile Strength in Air 212°F (100°C), 168 hr	-8.0 %	-8.0 %	ASTM D573
Change in Tensile Strength in Air 212°F (100°C), 168 hr	-8.0 %	-8.0 %	ISO 188
Change in Ultimate Elongation in Air 212°F (100°C), 168 hr	-11 %	-11 %	ASTM D573
Change in Tensile Strain at Break in Air 212°F (100°C), 168 hr	-11 %	-11 %	ISO 188

Flammability	Typical Value (English)	Typical Value (SI)	Test Based On
Flame Rating			UL 94
0.06 in (1.6 mm)	HB	HB	
0.08 in (2.1 mm)	HB	HB	

### Additional Information

Where applicable, test results based on fan gated, 2.0 mm injection molded plaques. Tensile strength, elongation and tensile stress are measured across the flow direction. Test results are generated by ExxonMobil test methods that may not fully conform to the ASTM and/or ISO methods. Test methods are available upon request. Compression set at 25% deflection. All products purchased directly from an ExxonMobil affiliate in Europe are REACH compliant. For products not imported into Europe by ExxonMobil, customers should assess their legal responsibilities under REACH.

### Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

For detailed Product Stewardship information, please contact Customer Service.

### Processing Statement

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Because of its inherent nature to bond, this material may, on occasion, agglomerate from shipping and storage. See Quick Processing Reference on 291-XXB150 and Tips from Technology - Guidelines for Storage and Handling of Santoprene TPV Bonding Grades.

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Santoprene™ 291-75B150  
Thermoplastic Vulcanizate

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)