# **ExconMobil**

# Vistalon™ 703 Ethylene Propylene Copolymer Rubber

Product Description       Key Features         Vistalon™ 703 EPDM rubber is a low Mooney viscosity, high ethylene content, crystalline copolymer of ethylene and propylene with a narrow molecular weight distribution. This product is sold in dense bale form.       Major applications include plastic modification such as the production of TPOs, as well as high heat resistant peroxide cured hoses, belts an molded mechanical goods such as seals and gaskets. Features include high green strength and excellent physical properties.         General <ul> <li>Availability<sup>1</sup></li> <li>Africa &amp; Middle East Asia Pacific</li> <li>Europe</li> <li>North America</li> <li>Latin America</li> </ul> Form(s)       Bale         Revision Date       10/05/2021         Physical       Typical Value (English)       Typical Value (SI)         Mooney Viscosity <sup>2</sup> (ML 1+4, 257°F (125°C))       21 MU       21 MU	Ethylene Content	73.0	wt%	73.0	wt%	ASTM D3900B
Vistalon™ 703 EPDM rubber is a low Mooney viscosity, high ethylene content, crystalline copolymer of ethylene and propylene with a narrow molecular weight distribution. This product is sold in dense bale form.       Major applications include plastic modification such as the production of TPOs, as well as high heat resistant peroxide cured hoses, belts an molded mechanical goods such as seals and gaskets. Features include high green strength and excellent physical properties.         General <ul> <li>Availability 1</li> <li>Africa &amp; Middle East Asia Pacific</li> <li>Asia Pacific</li> <li>Latin America</li> <li>North America</li> <li>Idots/2021</li> </ul>	Mooney Viscosity <sup>2</sup> (ML 1+4, 257°F (125°C	)) 21	MU	21	MU	
Vistalon™ 703 EPDM rubber is a low Mooney viscosity, high ethylene       Major applications include plastic modification such as the production of TPOs, as well as high heat resistant peroxide cured hoses, belts an molded mechanical goods such as seals and gaskets. Features include high green strength and excellent physical properties.         Seneral <ul> <li>Availability<sup>1</sup></li> <li>Africa &amp; Middle East</li> <li>Asia Pacific</li> <li>Latin America</li> <li>North America</li> </ul> Form(s)       Bale	Physical	Typical Value	(English)	Typical Value	(SI)	Test Based On
Vistalon™ 703 EPDM rubber is a low Mooney viscosity, high ethylene content, crystalline copolymer of ethylene and propylene with a narrow molecular weight distribution. This product is sold in dense bale form. General Availability <sup>1</sup> • Africa & Middle East • Asia Pacific • Europe • Latin America	Revision Date	• 10/05/2021				
Vistalon™ 703 EPDM rubber is a low Mooney viscosity, high ethylene content, crystalline copolymer of ethylene and propylene with a narrow molecular weight distribution. This product is sold in dense bale form. General Availability <sup>1</sup> • Africa & Middle East • Europe • North America	Form(s)	<ul> <li>Bale</li> </ul>				
Vistalon™ 703 EPDM rubber is a low Mooney viscosity, high ethylene content, crystalline copolymer of ethylene and propylene with a narrow molecular weight distribution. This product is sold in dense bale form. Major applications include plastic modification such as the production of TPOs, as well as high heat resistant peroxide cured hoses, belts an molded mechanical goods such as seals and gaskets. Features include high green strength and excellent physical properties.	Availability <sup>1</sup>				<ul> <li>North Arr</li> </ul>	nerica
Vistalon <sup>™</sup> 703 EPDM rubber is a low Mooney viscosity, high ethylene content, crystalline copolymer of ethylene and propylene with a narrow molecular weight distribution. This product is sold in dense bale form.	General					
Product Description Key Features	content, crystalline copolymer of ethylene a	and propylene with a na	rrow o rm. n	f TPOs, as well as high heat res nolded mechanical goods such	sistant peroxide cu as seals and gaske	ured hoses, belts an ets. Features includ
	Product Description		Key	/ Features		

## Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

For detailed Product Stewardship information, please contact Customer Service.

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

<sup>2</sup> Radial cavity dies, polymer remassed at 145±10°C.

#### For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com