

ExxonMobil™ LLDPE LL 8555 Series

Linear Low Density Polyethylene Resin

Product Description

LL 8555 is a linear low density hexene copolymer designed to offer superior processability, excellent dimensional control, whiteness and low warpage. This resin is ideally suited for applications that require excellent surface appearance and the optimum balance of ESCR, toughness and stiffness properties.

General

| | |
|---------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Availability ¹ | <ul style="list-style-type: none"> Latin America North America |
| Additive | <ul style="list-style-type: none"> LLP8555.25: Long Term UV-8 Stabilizer: Yes LL 8555.25: Long Term UV-8 Stabilizer: Yes |
| Applications | <ul style="list-style-type: none"> Consumer Articles Playground Equipment Potable Water Tanks Fine Threaded Containers Point of Display Cabinets Toys |
| Revision Date | <ul style="list-style-type: none"> 09/01/2014 |

| Resin Properties | Typical Value (English) | Typical Value (SI) | Test Based On |
|-------------------------------------------|-------------------------|-------------------------|------------------|
| Density | 0.936 g/cm ³ | 0.936 g/cm ³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg) | 6.8 g/10 min | 6.8 g/10 min | ASTM D1238 (mod) |

| Thermal | Typical Value (English) | Typical Value (SI) | Test Based On |
|-----------------------------------------------------------------|-------------------------|--------------------|---------------|
| Deflection Temperature Under Load (DTUL) at 66psi - Unannealed | 126 °F | 52 °C | ASTM D648 |
| Deflection Temperature Under Load (DTUL) at 264psi - Unannealed | 97 °F | 36 °C | ASTM D648 |
| Peak Melting Temperature | 259 °F | 126 °C | ASTM D3418 |

| Molded Properties | Typical Value (English) | Typical Value (SI) | Test Based On |
|-----------------------------------------------------|-------------------------|--------------------|---------------|
| Tensile Strength at Yield 2.0 in/min (50 mm/min) | 2300 psi | 16 MPa | ASTM D638 |
| Elongation at Yield (2.0 in/min (50 mm/min)) | 10 % | 10 % | ASTM D638 |
| Flexural Modulus - 1% Secant | 83000 psi | 570 MPa | ASTM D790B |
| Environmental Stress-Crack Resistance | | | ASTM D1693A |
| 10% Igepal, F50 | 50 hr | 50 hr | |
| 100% Igepal, F50 | > 1000 hr | > 1000 hr | |

| Impact | Typical Value (English) | Typical Value (SI) | Test Based On |
|-----------------------------------|-------------------------|--------------------|---------------|
| Impact Strength | | | ARM |
| -40°F (-40°C), 0.125 in (3.18 mm) | 59 ft-lb | 80 J | |
| -40°F (-40°C), 0.250 in (6.35 mm) | 150 ft-lb | 203 J | |

Additional Information

- All physical properties were measured on 3 mm. rotomolded samples unless a different value is shown, except for ESCR, which was measured on compression molded samples.
- Tensile testing was conducted at a crosshead speed of 50 mm/min. The tensile strength reported refers to the maximum stress reached during the test.
- Test procedures may be modified to accommodate operating conditions or facility limitations.

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ LLDPE LL 8555 Series
Linear Low Density Polyethylene Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com