ExxonMobil Signature Polymers

ExxonMobil™ C6LL 2042.48 Blown

C6 Linear Low Density Polyethylene

Product Description

ExxonMobil™ C6LL 2042.48 is an ethylene 1-hexene medium density polyethylene blown film resin for applications requiring high stiffness.It can also be used in cast films. Films produced from this resin exhibit good tensile and puncture resistance properties.

General

Availability [1]	▪ Latin America	▪ North America
Additive	▪ Antiblock: No ▪ Slip: No	▪ Processing Aid: No ▪ Thermal Stabilizer: Yes
Applications	▪ Agricultural Film ▪ Blown Film	▪ Diaper Backsheet ▪ Overwrap Film
Form(s)	▪ Pellets	
Revision Date	▪ 06/11/2020	

Resin Properties	Typical Value (English)		Typical Value (SI)		Test Based On
Density	0.942	g/cm³	0.942	g/cm³	ASTM D1505
Melt Index (190°C/2.16 kg)	2.0	g/10 min	2.0	g/10 min	ASTM D1238
Peak Melting Temperature	264	°F	129	°C	ExxonMobil Method

Thermal	Typical Value (English)		Typical Value (SI)		Test Based On
Vicat Softening Temperature	248	°F	120	°C	ExxonMobil Method

Film Properties	Typical Value (English)		Typical Value (SI)		Test Based On
Tensile Strength at Yield MD	2800	psi	19	MPa	ASTM D882
Tensile Strength at Yield TD	3500	psi	24	MPa	ASTM D882
Tensile Strength at Break MD	6400	psi	44	MPa	ASTM D882
Tensile Strength at Break TD	5900	psi	41	MPa	ASTM D882
Elongation at Break MD	760	%	760	%	ASTM D882
Elongation at Break TD	990	%	990	%	ASTM D882
Secant Modulus MD - 1% Secant	78000	psi	540	MPa	ASTM D882
Secant Modulus TD - 1% Secant	100000	psi	710	MPa	ASTM D882
Dart Drop Impact	< 60	g	< 60	g	ASTM D1709A
Elmendorf Tear Strength MD	20	g	20	g	ASTM D1922
Elmendorf Tear Strength TD	110	g	110	g	ASTM D1922
Puncture Force	5	lbf	22	N	ExxonMobil Method
Puncture Energy	3.7	in·lb	0.42	J	ExxonMobil Method

Optical Properties	Typical Value (English)		Typical Value (SI)		Test Based On
Gloss (45°)	29		29		ASTM D2457
Haze	22	%	22	%	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Film (1.0 mil/25.4 micron) made on a 2.5 inch (63.5 mm) blown film line with a 2.5:1 blow-up ratio, a melt temperature of 395-415°F (202-213°C), a 60 mil (1.52 mm) die gap at a rate of 10 lbs/hr/in die circumference (1.79 kg/hr/cm).

ExxonMobil™ C6LL 2042.48 Blown
C6 Linear Low Density Polyethylene

Notes

Typical properties: these are not to be construed as specifications.

[1] Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: Contact Us

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com