

Geolast™ 701-80W183

Thermoplastic Vulcanizate

Product Description		Key Features		
<p>A soft, black, oil resistant thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good hot air and hot oil resistance for use in a wide range of applications. This grade of Geolast TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion or blow molding. It is polyolefin based and recyclable within the manufacturing stream.</p>		<ul style="list-style-type: none"> Recyclable. Designed for improved fluid resistance. 		
General				
Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Europe 	<ul style="list-style-type: none"> Latin America North America 		
Applications	<ul style="list-style-type: none"> Automotive - Seals and Gaskets 	<ul style="list-style-type: none"> Oil Resistant Seals and Gaskets 		
Uses	<ul style="list-style-type: none"> Automotive Applications 	<ul style="list-style-type: none"> Industrial Applications 		
RoHS Compliance	<ul style="list-style-type: none"> RoHS Compliant 			
Color	<ul style="list-style-type: none"> Black 			
Form(s)	<ul style="list-style-type: none"> Pellets 			
Processing Method	<ul style="list-style-type: none"> Blow Molding Coextrusion Extrusion 	<ul style="list-style-type: none"> Extrusion Blow Molding Injection Blow Molding Injection Molding 	<ul style="list-style-type: none"> Multi Injection Molding Profile Extrusion Sheet Extrusion 	
Revision Date	<ul style="list-style-type: none"> 06/17/2014 			
Physical				
	Typical Value (English)	Typical Value (SI)	Test Based On	
Density / Specific Gravity	1.03	1.03	ASTM D792	
Density	1.03 g/cm ³	1.03 g/cm ³	ISO 1183	
Hardness				
	Typical Value (English)	Typical Value (SI)	Test Based On	
Shore Hardness			ISO 868	
Shore A, 15 sec, 73°F (23°C)	83	83		
Elastomers				
	Typical Value (English)	Typical Value (SI)	Test Based On	
Tensile Stress at 100% - Across Flow (73°F (23°C))	754 psi	5.20 MPa	ASTM D412	
Tensile Stress at 100% - Across Flow (73°F (23°C))	754 psi	5.20 MPa	ISO 37	
Tensile Strength at Break - Across Flow (73°F (23°C))	1280 psi	8.80 MPa	ASTM D412	
Tensile Stress at Break - Across Flow (73°F (23°C))	1280 psi	8.80 MPa	ISO 37	
Elongation at Break - Across Flow (73°F (23°C))	290 %	290 %	ASTM D412	
Tensile Strain at Break - Across Flow (73°F (23°C))	290 %	290 %	ISO 37	
Compression Set			ASTM D395B	
158°F (70°C), 22 hr, Type 1	30 %	30 %		
257°F (125°C), 70 hr, Type 1	47 %	47 %		
Compression Set			ISO 815	
158°F (70°C), 22 hr, Type A	30 %	30 %		
257°F (125°C), 70 hr, Type A	47 %	47 %		
Thermal				
	Typical Value (English)	Typical Value (SI)	Test Based On	
Brittleness Temperature	-26 °F	-32 °C	ASTM D746	
Brittleness Temperature	-26 °F	-32 °C	ISO 812	

Geolast™ 701-80W183

Thermoplastic Vulcanizate

Injection Notes

Geolast TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Injection Molding Guide.

Extrusion Notes

Geolast TPV is incompatible with acetal and PVC. For more information regarding processing and die design, please consult our Extrusion Guide.

Aging	Typical Value (English)	Typical Value (SI)	Test Based On
Change in Tensile Strength in Air 257°F (125°C), 168 hr	6.0 %	6.0 %	ASTM D573
Change in Tensile Strength in Air 257°F (125°C), 168 hr	6.0 %	6.0 %	ISO 188
Change in Ultimate Elongation in Air 257°F (125°C), 168 hr	-37 %	-37 %	ASTM D573
Change in Tensile Strain at Break in Air 257°F (125°C), 168 hr	-37 %	-37 %	ISO 188
Change in Durometer Hardness in Air Shore A, 257°F (125°C), 168 hr	2.0	2.0	ASTM D573
Change in Shore Hardness in Air Shore A, 257°F (125°C), 168 hr	2.0	2.0	ISO 188

Additional Information

Where applicable, test results based on fan gated, injection molded plaques.

Tensile strength, elongation and tensile stress are measured across the flow direction - ISO type 1, ASTM die C.

Compression set at 25% deflection.

This product may be manufactured by a third party under contract with Exxon Mobil Corporation or one of its affiliates, pursuant to a quality management system which complies with the requirements of ISO 9001:2015.

All products purchased directly from an ExxonMobil affiliate in Europe are REACH compliant. For products not imported into Europe by ExxonMobil, customers should assess their legal responsibilities under REACH.

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

For detailed Product Stewardship information, please contact Customer Service.

Processing Statement

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Geolast TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC. The melt temperature should be maintained below 215°C (420°F). For more information, please consult our Safety Data Sheet, Injection Molding Guide and Extrusion Guide.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Geolast™ 701-80W183
Thermoplastic Vulcanizate

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com