

Vistamaxx™ Performance Polymer 6102

Propylene Elastomer

Product Description		Key Features		
<p>Vistamaxx 6102 is primarily composed of isotactic propylene repeat units with random ethylene distribution, and is produced using ExxonMobil's proprietary metallocene catalyst technology. It has excellent elastomeric properties, is easy to process and is compatible with a wide variety of materials. It is particularly good for thermoplastic and polyolefinic blends where a balance of flexibility, transparency and impact performance is required.</p>		<ul style="list-style-type: none"> ▪ Suitable for a wide range of film and compounding applications. ▪ Other typical applications include calendered or extruded profiles, foamed or blown molded goods and thermoformed products. ▪ Excellent adhesion to conventional or metallocene PP and PE. ▪ Very good elasticity, toughness and melt strength. ▪ Very low seal initiation temperature combined with high seal strength when used as sealing layer of co-extruded structures. ▪ Very good chemical resistance and long term aging. ▪ RoHS compliant. 		
General				
Availability ¹	<ul style="list-style-type: none"> ▪ Africa & Middle East ▪ Asia Pacific 	<ul style="list-style-type: none"> ▪ Europe ▪ Latin America 	<ul style="list-style-type: none"> ▪ North America 	
Applications	<ul style="list-style-type: none"> ▪ Blown Film ▪ Blown Molded Goods ▪ Calendered Profiles 	<ul style="list-style-type: none"> ▪ Cast Film ▪ Extruded Profiles ▪ Foamed Goods 	<ul style="list-style-type: none"> ▪ PP/TPE Modification 	
Uses	<ul style="list-style-type: none"> ▪ Compounding 	<ul style="list-style-type: none"> ▪ Film 	<ul style="list-style-type: none"> ▪ Packaging 	
RoHS Compliance	<ul style="list-style-type: none"> ▪ RoHS Compliant 			
Form(s)	<ul style="list-style-type: none"> ▪ Pellets 			
Revision Date	<ul style="list-style-type: none"> ▪ 07/14/2020 			
Physical				
Density ²	Typical Value (English)	Typical Value (SI)	Test Based On	
	0.862 g/cm ³	0.862 g/cm ³	ExxonMobil Method	
Melt Index ² (190°C/2.16 kg)	1.4 g/10 min	1.4 g/10 min	ASTM D1238	
Melt Mass-Flow Rate (MFR) ² (230°C/2.16 kg)	3.0 g/10 min	3.0 g/10 min	ExxonMobil Method	
Ethylene Content	16 wt%	16 wt%	ExxonMobil Method	
Hardness				
Durometer Hardness (Shore A)	Typical Value (English)	Typical Value (SI)	Test Based On	
	67	67	ExxonMobil Method	
Mechanical				
Tensile Stress at 100%	Typical Value (English)	Typical Value (SI)	Test Based On	
	320 psi	2.2 MPa	ExxonMobil Method	
Tensile Stress at 300%	400 psi	2.8 MPa	ExxonMobil Method	
Tensile Strength at Break	> 1100 psi	> 7.6 MPa	ExxonMobil Method	
Tensile Set	12 %	12 %	ExxonMobil Method	
Elongation at Break	> 800 %	> 800 %	ExxonMobil Method	
Flexural Modulus - 1% Secant	2100 psi	14 MPa	ExxonMobil Method	
Elastomers				
Tear Strength (Die C)	Typical Value (English)	Typical Value (SI)	Test Based On	
	190 lbf/in	33.3 kN/m	ExxonMobil Method	
Thermal				
Vicat Softening Temperature	Typical Value (English)	Typical Value (SI)	Test Based On	
	129 °F	53.9 °C	ExxonMobil Method	

Vistamaxx™ Performance Polymer 6102

Propylene Elastomer

Additional Information

Please contact Customer Service for food law compliance information.

For data specific to chemical resistance, refer to the Technical Literature (TL), Chemical Resistance of Vistamaxx Performance Polymer.

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

Processing Statement

Vistamaxx polymers have a wide temperature processing window. A good starting point for temperatures is 10°C above the highest melting point. This material does not require drying and can be compounded or used in a dry blend. Use conventional processing knowledge to ensure mixing of the materials.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

² Property specified in conventional unit of measure.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com