

Exceed™ Stiff m 3527.PA

(Legacy name: Exceed™ 3527PA)

Metallocene Polyethylene

Product Description

Exceed™ Stiff m 3527.PA is an ethylene 1-hexene copolymer. Films made of Exceed Stiff m 3527.PA have high modulus and outstanding tensile, impact and puncture resistance properties. These superior properties together with excellent drawability make this a versatile polymer for mono layer and multi-layer cast stretch film applications. TnPP is not intentionally added to Exceed Stiff m 3527.PA.

General

Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America
Additive	Exceed™ Stiff m 3527.PA: Antiblock: No; Slip: No; Processing Aid: No; Thermal Stabilizer: Yes		
Applications	<ul style="list-style-type: none"> Artificial grass Cast Film Cast Stretch Film 	<ul style="list-style-type: none"> Diaper Backsheet Hygiene film Overwrap Film 	<ul style="list-style-type: none"> Personal Care
Form(s)	Pellets		
Revision Date	05/22/2018		

Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.927 g/cm ³	0.927 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	3.5 g/10 min	3.5 g/10 min	ASTM D1238
Peak Melting Temperature	250 °F	121 °C	ExxonMobil Method

Film Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	1500 psi	10 MPa	ASTM D882
Tensile Strength at Yield TD	1400 psi	9.6 MPa	ASTM D882
Tensile Strength at Break MD	8900 psi	60 MPa	ASTM D882
Tensile Strength at Break TD	5900 psi	41 MPa	ASTM D882
Elongation at Break MD	530 %	530 %	ASTM D882
Elongation at Break TD	750 %	750 %	ASTM D882
Secant Modulus MD - 1% Secant	27000 psi	190 MPa	ASTM D882
Secant Modulus TD - 1% Secant	30000 psi	200 MPa	ASTM D882
Dart Drop Impact	60 g	60 g	ASTM D1709A
Elmendorf Tear Strength MD	70 g	70 g	ASTM D1922
Elmendorf Tear Strength TD	400 g	400 g	ASTM D1922
Puncture Force	10 lbf	45 N	ExxonMobil Method
Puncture Energy	23 in-lb	2.6 J	ExxonMobil Method

Optical Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	87	87	ASTM D2457
Haze	2.8 %	2.8 %	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Tris(nonylphenol)phosphite (TNPP) CAS# 26523-78-4 is not intentionally used by ExxonMobil in this product. Although this product is not routinely tested for its presence, based on product composition knowledge this substance is not expected to be present. However, the fact that this substance is not intentionally used by ExxonMobil in this product does not exclude that trace levels of this substance may be present as a result of the specific characteristics of the raw materials and/or of the manufacturing process.

Processing Statement

Film (0.8 mil / 20 micron) made from Exceed™ Stiff m 3527.PA on a Black Clawson 3.5 inch cast line at a 5.5 inch melt curtain length, 520-580°F melt temperature, 80°F chill roll temperature and 750 fpm line speed. Films were aged at 140°F for 48 hours before lab aging and testing.

Exceed™ Stiff m 3527.PA
Metallocene Polyethylene**Notes**

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com