

Escorene™ Ultra UL 7510

Ethylene Vinyl Acetate Copolymer Resin

Product Description

Escorene Ultra UL 7510 is a very high flow, 18.7% VA copolymer that has very good compatibility with hydrocarbon tackifiers and most waxes. It is suitable for making hot melt adhesives, sealants and wax blends.

General

Availability ¹	▪ Asia Pacific	▪ Latin America	▪ North America
Additive	▪ Antiblock: No	▪ Slip: No	▪ Thermal Stabilizer: Yes
Applications	▪ Adhesives and Sealants ▪ Hot Melt Adhesives	▪ Industrial Sealants ▪ Wax Blends	
Form(s)	▪ Pellets		
Revision Date	▪ 06/11/2020		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.933 g/cm ³	0.933 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	500 g/10 min	500 g/10 min	ASTM D1238
Vinyl Acetate Content	18.7 wt%	18.7 wt%	ExxonMobil Method
Peak Melting Temperature	169 °F	76 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	100 °F	38.0 °C	ExxonMobil Method

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break	510 psi	3.5 MPa	ExxonMobil Method
Elongation at Break	98 %	98 %	ExxonMobil Method
Flexural Modulus - 1% Secant	5000 psi	35 MPa	ExxonMobil Method
Durometer Hardness			ExxonMobil Method
Shore A, 15 sec	84	84	
Shore D, 15 sec	24	24	

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

All physical properties were measured on compression molded specimens.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Escorene™ Ultra UL 7510
Ethylene Vinyl Acetate Copolymer Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com