

Exxtral™ Performance Polyolefin CMU236

Polypropylene, Compounded (TPO)

Product Description

A specialty thermoplastic polyolefin resin designed for automotive interior covered applications such as retainers in which a good stiffness/toughness balance and low emissions are required.

| General | | | | | |
|--|------------------------|------------------------|----------------------------|----------------------------|----------------------|
| Availability ¹ | · Africa & Middle East | | • Europe | | |
| Features | Balanced Stiffness/T | oughness • | Good Dimensional Stability | y • Medium | n Impact Resistance |
| Uses | · Automotive Interior | Parts • | Automotive Interior Trim | Automo | otive Under the Hood |
| Appearance | Black | | | | |
| Form(s) | • Pellets | | | | |
| Processing Method | Injection Molding | | | | |
| Revision Date | 12/17/2020 | | | | |
| Physical | Typical Value | (English) | Typical Value | (SI) | Test Based On |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg |) 16 | g/10 min | 16 | g/10 min | ISO 1133 |
| Melt Volume-Flow Rate (MVR) (230°C/2.16 kg) | 18 | cm ³ /10min | 18 | cm ³ /10min | ISO 1133 |
| Density | 1.05 | g/cm³ | 1.05 | g/cm³ | ISO 1183 |
| Mechanical | Typical Value | (English) | Typical Value | (SI) | Test Based On |
| Tensile Stress at Yield | 3420 | psi | 23.6 | | ISO 527-2/50 |
| Tensile Strain at Yield | 3.1 | % | 3.1 | | ISO 527-2/50 |
| Tensile Modulus - Secant (73°F (23°C)) | 351000 | psi | 2420 | MPa | ISO 527-1 |
| Impact | Typical Value | (English) | Typical Value | (SI) | Test Based On |
| Charpy Notched Impact Strength | 71 | , , , | 71 | , , | ISO 179 |
| 32°F (0°C), Complete Break | 1.5 | ft·lb/in² | 3.2 | kJ/m² | |
| 73°F (23°C), Complete Break | 3.6 | ft·lb/in² | 7.6 | kJ/m² | |
| Thermal | Typical Value | (English) | Typical Value | (SI) | Test Based On |
| Heat Deflection Temperature (1.80 MPa) | 136 | °F | 58.0 | °C | ISO 75-2/A |
| Heat Deflection Temperature (0.45 MPa) | 230 | °F | 110 | °C | ISO 75-2/B |

Legal Statement

This product is not intended for use in food contact application.

This product is not intended for use in medical applications and should not be used in any such applications.

Notes

Typical properties: these are not to be construed as specifications.

Effective Date: 12/17/2020 ExxonMobil Page: 1 of 2

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.



Exxtral[™] Performance Polyolefin CMU236 Polypropylene, Compounded (TPO)

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2023 ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com

Effective Date: 12/17/2020 ExxonMobil Page: 2 of 2