

ExxonMobil™ LDPE LD 160AT

Low Density Polyethylene Resin

Product Description

LD 160 series are LDPE grades, which offer good draw down and optical properties.

General

| | | | |
|---------------------------|------------------------------------|----------------------------------|-------------------------------------|
| Availability ¹ | ▪ Africa & Middle East | ▪ Asia Pacific | |
| Additive | ▪ Antiblock: 1200 ppm | ▪ Slip: 900 ppm | ▪ Thermal Stabilizer: Yes |
| Applications | ▪ Cast Film ▪ High Clarity Film | ▪ Laundry Film ▪ Produce Bags | ▪ Profile Extrusion ▪ Zipper Bag |
| Revision Date | ▪ 01/01/2017 | | |

| Resin Properties | Typical Value (English) | Typical Value (SI) | Test Based On |
|----------------------------|-------------------------|-------------------------|-------------------|
| Density | 0.923 g/cm ³ | 0.923 g/cm ³ | ASTM D1505 |
| Melt Index (190°C/2.16 kg) | 4.0 g/10 min | 4.0 g/10 min | ASTM D1238 |
| Peak Melting Temperature | 226 °F | 108 °C | ExxonMobil Method |

| Film Properties | Typical Value (English) | Typical Value (SI) | Test Based On |
|-------------------------------|-------------------------|--------------------|---------------|
| Tensile Strength at Yield MD | 1500 psi | 10 MPa | ASTM D882 |
| Tensile Strength at Yield TD | 1400 psi | 9.6 MPa | ASTM D882 |
| Tensile Strength at Break MD | 3300 psi | 23 MPa | ASTM D882 |
| Tensile Strength at Break TD | 2200 psi | 15 MPa | ASTM D882 |
| Elongation at Break MD | 180 % | 180 % | ASTM D882 |
| Elongation at Break TD | 490 % | 490 % | ASTM D882 |
| Secant Modulus MD - 1% Secant | 25000 psi | 170 MPa | ASTM D882 |
| Secant Modulus TD - 1% Secant | 30000 psi | 210 MPa | ASTM D882 |
| Dart Drop Impact | 70 g | 70 g | ASTM D1709A |
| Elmendorf Tear Strength MD | 290 g | 290 g | ASTM D1922 |
| Elmendorf Tear Strength TD | 110 g | 110 g | ASTM D1922 |

| Optical Properties | Typical Value (English) | Typical Value (SI) | Test Based On |
|--------------------|-------------------------|--------------------|---------------|
| Gloss (45°) | 71 | 71 | ASTM D2457 |
| Haze | 5.2 % | 5.2 % | ASTM D1003 |

Additional Information

LD 160 AT can - in principle - be used in food contact applications in various EU Member States and in the USA (FDA). Migrations or use limitations may apply. Please contact your ExxonMobil Chemical representative for more detailed information and/or actual compliance certification documents for the specific grade of interest.

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Processing Statement

The test specimen were prepared on LD 160AT, 30µm (1.18 mil) thick film, using a 200 mm (7.9 in) die, die gap of 1.0 mm (39.4 mil), Blow-Up Ratio of 2.5 and temperature profile of 180 - 190°C (356 - 374°F) 338°F).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ LDPE LD 160AT
Low Density Polyethylene Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com