

Achieve™ Advanced PP8285E1

Polypropylene Impact Copolymer

Product Description

A high crystallinity, high impact copolymer resin designed for injection molded applications requiring excellent processing attributes.

General

Availability ¹	▪ Asia Pacific	▪ North America	
Features	▪ Balanced Stiffness/Toughness ▪ Good Impact Resistance	▪ Good Processability ▪ Heat Aging Resistant	▪ Nucleated
Uses	▪ Appliance Components	▪ Automotive Applications	▪ Industrial Applications
Appearance	▪ Natural Color		
Form(s)	▪ Pellets		
Processing Method	▪ Compounding	▪ Injection Molding	
Revision Date	▪ 01/01/2017		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	30 g/10 min	30 g/10 min	ASTM D1238
Density	0.900 g/cm ³	0.900 g/cm ³	ExxonMobil Method

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 2.0 in/min (51 mm/min)	2940 psi	20.3 MPa	ASTM D638
Tensile Stress at Yield	2890 psi	19.9 MPa	ISO 527-2
Elongation at Yield	5.7 %	5.7 %	ASTM D638
Tensile Strain at Yield	5.0 %	5.0 %	ISO 527-2
Flexural Modulus - 1% Secant 0.051 in/min (1.3 mm/min)	144000 psi	993 MPa	ASTM D790A
0.51 in/min (13 mm/min)	164000 psi	1130 MPa	ASTM D790B
Flexural Modulus (0.079 in/min (2.0 mm/min))	148000 psi	1020 MPa	ISO 178

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact 0°F (-18°C)	1.7 ft-lb/in	89 J/m	ASTM D256A
73°F (23°C)	No Break	No Break	
Notched Izod Impact Strength -4°F (-20°C)	3.2 ft-lb/in ²	6.8 kJ/m ²	ISO 180/1A
73°F (23°C)	22 ft-lb/in ²	46 kJ/m ²	
Gardner Impact -20°F (-29°C), 0.125 in (3.18 mm), Geometry GC	292 in-lb	33.0 J	ASTM D5420

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Heat Deflection Temperature (0.45 MPa)	181 °F	82.8 °C	ISO 75-2/B
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	198 °F	92.0 °C	ASTM D648

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

This product is not intended for use in food contact application.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Achieve™ Advanced PP8285E1
Polypropylene Impact Copolymer

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com