

ExxonMobil™ HD 5805

High Density Polyethylene

Product Description

ExxonMobil™ HD 5805 is a high density polyethylene resin that can be processed on high stalk, pocket extrusion or cast lines. Films made from HD 5805 resin exhibit an excellent stiffness balance. High thermal stability provides excellent film appearance and high quality recycle. HD 5805 resin is particularly recommended as a blend component with LLDPE for stiff clear films.

General

Availability ¹	▪ Latin America	▪ North America	
Additive	▪ Antiblock: No	▪ Slip: No	▪ Thermal Stabilizer: Yes
Applications	▪ Blown Film ▪ Deli Wrap ▪ Food Packaging	▪ Heavy Duty Bags ▪ Oriented Film Products ▪ Overwrap Film	▪ Surface Protection Film
Form(s)	▪ Pellets		
Revision Date	▪ 04/01/2019		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.958 g/cm ³	0.958 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	0.45 g/10 min	0.45 g/10 min	ASTM D1238
High Load Melt Index (190°C/21.6 kg)	28 g/10 min	28 g/10 min	ASTM D1238
Peak Melting Temperature	270 °F	132 °C	ExxonMobil Method

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	4800 psi	33 MPa	ASTM D882
Tensile Strength at Yield TD	5200 psi	36 MPa	ASTM D882
Tensile Strength at Break MD	11000 psi	70 MPa	ASTM D882
Tensile Strength at Break TD	5600 psi	39 MPa	ASTM D882
Elongation at Break MD	400 %	400 %	ASTM D882
Elongation at Break TD	6 %	6 %	ASTM D882
Secant Modulus MD - 1% Secant	150000 psi	1000 MPa	ASTM D882
Secant Modulus TD - 1% Secant	220000 psi	1500 MPa	ASTM D882
Dart Drop Impact	< 60 g	< 60 g	ASTM D1709A
Elmendorf Tear Strength MD	10 g	10 g	ASTM D1922
Elmendorf Tear Strength TD	1200 g	1200 g	ASTM D1922

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Film (1.0 mil/25.4 micron) made from HD 5805 resin on a 2.5 inch (63.5 mm) blown film line with a 2.5:1 blow-up ratio, a melt temperature of 405-425°F (207-218°C), a 60 mil (1.5 mm) die gap at a rate of 10 lbs/hr/in die circumference (1.79 kg/hr/cm).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ HD 5805
High Density Polyethylene

[For additional technical, sales and order assistance: Contact Us](#)

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com