

ExxonMobil™ LD 9519.LN

(Legacy name: ExxonMobil™ LDPE LD 516.LN)

Low Density Polyethylene

Product Description

ExxonMobil™ LD 9519.LN is a medium MI, low density polyethylene resin designed for use in color concentrates and masterbatches. Its flow properties ensure improved processability and uniform dispersion of additives. This resin also offers an outstanding balance of processability and end use performance for injection molding applications.

General

Availability ¹	<ul style="list-style-type: none"> Latin America North America
Additive	<ul style="list-style-type: none"> Antiblock: No Slip: No Thermal Stabilizer: No
Applications	<ul style="list-style-type: none"> Caps Closures Compounding Food Packaging Containers Houseware Articles Injection Molding Masterbatch Base Resin
Form(s)	<ul style="list-style-type: none"> Pellets
Revision Date	<ul style="list-style-type: none"> 06/17/2020

Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.919 g/cm ³	0.919 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	9.5 g/10 min	9.5 g/10 min	ASTM D1238
Peak Melting Temperature	228 °F	109 °C	ExxonMobil Method

Thermal

	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	185 °F	85.0 °C	ExxonMobil Method

Molded Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield	1700 psi	12 MPa	ExxonMobil Method
Tensile Strength at Break	1200 psi	8.6 MPa	ExxonMobil Method
Elongation at Yield	60 %	60 %	ExxonMobil Method
Elongation at Break	87 %	87 %	ExxonMobil Method
Flexural Modulus - 1% Secant	33000 psi	230 MPa	ExxonMobil Method
Durometer Hardness			ExxonMobil Method
Shore A, 15 sec	94	94	
Shore D, 15 sec	45	45	

Impact

	Typical Value (English)	Typical Value (SI)	Test Based On
Instrumented Dart Impact			ExxonMobil Method
-40°F (-40°C)	14 ft·lb	20 J	
73°F (23°C)	12 ft·lb	16 J	

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

All physical properties were measured on compression molded specimens.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ LD 9519.LN

Low Density Polyethylene

For additional technical, sales and order assistance: [Contact Us](#)

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com