

ExxonMobil™ LD 12015.BA

Low Density Polyethylene

Product Description

ExxonMobil™ LD 12015.BA is an LDPE extrusion coating grade especially designed for coating on non-woven substrates. Its high melt-index combined with low density gives this grade the right balance between adhesion onto non-wovens, flexibility after coating and acts as a barrier for fluids and gases. ExxonMobil™ LD 12015.BA can also be used as a general extrusion and co-extrusion coating grade that requires easy processability, good neck-in/draw down balance and excellent heat sealability.

General

| | | | |
|---------------------------|---|--|---|
| Availability ¹ | ▪ Africa & Middle East | ▪ Europe | |
| Additive | ▪ Antiblock: No | ▪ Slip: No | ▪ Thermal Stabilizer: No |
| Applications | ▪ Coextrusion Coating ▪ Demanding Heat Seals ▪ Document Plastification ▪ Extrusion Coating | ▪ Extrusion Lamination ▪ Food Packaging ▪ High Speed, Thin Weight Coatings ▪ Industrial Packaging | ▪ Non-Woven Coating ▪ Photographic Paper ▪ Thermal Lamination |
| Revision Date | ▪ 04/01/2018 | | |

Resin Properties

| | Typical Value (English) | Typical Value (SI) | Test Based On |
|---|-------------------------|-------------------------|-------------------|
| Density | 0.915 g/cm ³ | 0.915 g/cm ³ | ASTM D1505 |
| Melt Index ² (190°C/2.16 kg) | 12 g/10 min | 12 g/10 min | ASTM D1238 |
| Peak Melting Temperature | 217 °F | 103 °C | ExxonMobil Method |

Coating Properties

| | Typical Value (English) | Typical Value (SI) | Test Based On |
|--|-------------------------|--------------------|-------------------|
| Draw Down | | | ExxonMobil Method |
| Constant output at 35 rpm, 599°F (315°C) | 420 m/min | 420 m/min | |
| Neck-in | | | ExxonMobil Method |
| 328 ft/min (100 m/min), Constant output at 35 rpm, 599°F (315°C) | 1.8 in | 4.6 cm | |
| 656 ft/min (200 m/min), Constant output at 35 rpm, 599°F (315°C) | 1.7 in | 4.4 cm | |

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Typical values obtained on a pilot co-extrusion line at ExxonMobil Chemical Europe Technical Center at an air gap of 170 mm (6.7 in).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

² Value reported is an estimate based on ExxonMobil's correlation from melt flow rate data measured at other standard conditions, based on ASTM D 1238.

ExxonMobil™ LD 12015.BA
Low Density Polyethylene

[For additional technical, sales and order assistance: Contact Us](#)

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com