

ExxonMobil™ PP5722E1

Polypropylene Homopolymer

Product Description

A medium flow homopolymer resin designed for mono-oriented products like stretched tapes and monofilament.

General

Availability ¹	▪ Asia Pacific	
Features	▪ Good Gauge Control ▪ Good Processability	▪ Low Water Carryover ▪ Medium Flow
Uses	▪ Fabrics ▪ Rope	▪ Tape ▪ Yarn
Appearance	▪ Natural Color	
Form(s)	▪ Pellets	
Processing Method	▪ Extrusion	
Revision Date	▪ 07/01/2019	

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0 g/10 min	4.0 g/10 min	ASTM D1238
Density	0.900 g/cm ³	0.900 g/cm ³	ExxonMobil Method

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 2.0 in/min (51 mm/min)	5190 psi	35.8 MPa	ASTM D638
Tensile Stress at Yield	4960 psi	34.2 MPa	ISO 527-2/50
Elongation at Yield (2.0 in/min (50 mm/min))	8.9 %	8.9 %	ASTM D638
Tensile Strain at Yield	9.2 %	9.2 %	ISO 527-2/50
Flexural Modulus - 1% Secant 0.051 in/min (1.3 mm/min)	235000 psi	1620 MPa	ASTM D790A
0.51 in/min (13 mm/min)	270000 psi	1860 MPa	ASTM D790B
Flexural Modulus (0.079 in/min (2.0 mm/min))	234000 psi	1610 MPa	ISO 178

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact (73°F (23°C))	0.61 ft-lb/in	33 J/m	ASTM D256A
Notched Izod Impact Strength (73°F (23°C))	2.5 ft-lb/in ²	5.3 kJ/m ²	ISO 180/1A
Charpy Notched Impact Strength (73°F (23°C))	2.5 ft-lb/in ²	5.2 kJ/m ²	ISO 179/1eA

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Heat Deflection Temperature (1.80 MPa) Flatwise	126 °F	52.0 °C	ExxonMobil Method
Heat Deflection Temperature (0.45 MPa) Flatwise	197 °F	91.7 °C	ExxonMobil Method
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	204 °F	95.6 °C	ExxonMobil Method

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Rockwell Hardness	111	111	ASTM D785

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

ExxonMobil™ PP5722E1
Polypropylene Homopolymer

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com