

ExxonMobil™ HDPE HTA 001HD5

High Density Polyethylene (HMW) Resin

Product Description

HTA 001HD5 is a high molecular weight HDPE film grade. Films made from HTA 001HD5 exhibit excellent impact and toughness properties as well as high stiffness.

General

Availability ¹	▪ Africa & Middle East	▪ Asia Pacific	
Additive	▪ Antiblock: No	▪ Slip: No	▪ Thermal Stabilizer: Yes
Applications	▪ Blown Film ▪ Grocery Sacks ▪ Liners	▪ Produce Bags ▪ Produce Bags On A Roll ▪ Refuse Bags	▪ Thin Gauged Consumer Bags ▪ Trash Can Liners
Revision Date	▪ 09/15/2016		

Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.952 g/cm ³	0.952 g/cm ³	ASTM D1505
High Load Melt Index (190°C/21.6 kg)	9.0 g/10 min	9.0 g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	0.32 g/10 min	0.32 g/10 min	ASTM D1238

Thermal

	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	259 °F	126 °C	ASTM D1525

Film Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	5900 psi	41 MPa	ASTM D882
Tensile Strength at Yield TD	4400 psi	30 MPa	ASTM D882
Tensile Strength at Break MD	8600 psi	60 MPa	ASTM D882
Tensile Strength at Break TD	8100 psi	60 MPa	ASTM D882
Elongation at Break MD	220 %	220 %	ASTM D882
Elongation at Break TD	430 %	430 %	ASTM D882
Secant Modulus MD - 1% Secant	170000 psi	1200 MPa	ASTM D882
Secant Modulus TD - 1% Secant	170000 psi	1200 MPa	ASTM D882
Dart Drop Impact	190 g	190 g	ASTM D1709A
Elmendorf Tear Strength MD	8 g	8 g	ASTM D1922
Elmendorf Tear Strength TD	30 g	30 g	ASTM D1922

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Processing Statement

The film properties have been measured on 15 µm (0.59 mil) thick films with a blow-up ratio of 4 : 1 and a frostline height of 9 x die diameter (die diameter/ gap: 120mm/1.5mm (4.7 in/0.06 in); 215°C (419°F) melt temperature; 70 kg/hr (154 lb/hr) output).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ HDPE HTA 001HD5
High Density Polyethylene (HMW) Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com