

ExxonMobil™ C4LL 2818.AY Cast

C4 Linear Low Density Polyethylene

Product Description

ExxonMobil™ C4LL 2818.AY is an ethylene 1-butene copolymer resin, offering excellent high temperature stability. Properties may be further enhanced by combining with Exceed™ mLLDPE. TnPP is not intentionally added to ExxonMobil™ C4LL 2818.AY resin.

General

Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	
Additive	<ul style="list-style-type: none"> Antiblock: No 	<ul style="list-style-type: none"> Slip: No 	<ul style="list-style-type: none"> Thermal Stabilizer: Yes
Applications	<ul style="list-style-type: none"> Cast Film Cast Stretch Film 	<ul style="list-style-type: none"> Food Packaging Form Fill And Seal Packaging 	<ul style="list-style-type: none"> General Packaging
Revision Date	<ul style="list-style-type: none"> 06/30/2016 		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.918 g/cm ³	0.918 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	2.8 g/10 min	2.8 g/10 min	ASTM D1238
Peak Melting Temperature	248 °F	120 °C	ExxonMobil Method

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	7400 psi	50 MPa	ASTM D882
Tensile Strength at Break TD	3300 psi	23 MPa	ASTM D882
Elongation at Break MD	530 %	530 %	ASTM D882
Elongation at Break TD	840 %	840 %	ASTM D882
Secant Modulus MD - 1% Secant	20000 psi	140 MPa	ASTM D882
Secant Modulus TD - 1% Secant	21000 psi	150 MPa	ASTM D882
Dart Drop Impact	40 g	40 g	ASTM D1709A
Elmendorf Tear Strength MD	40 g	40 g	ASTM D1922
Elmendorf Tear Strength TD	340 g	340 g	ASTM D1922

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	95	95	ASTM D2457
Haze	1.7 %	1.7 %	ASTM D1003

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Tris(nonylphenol)phosphite (TNPP) CAS# 26523-78-4 is not intentionally used by ExxonMobil in this product. Although this product is not routinely tested for its presence, based on product composition knowledge this substance is not expected to be present. However, the fact that this substance is not intentionally used by ExxonMobil in this product does not exclude that trace levels of this substance may be present as a result of the specific characteristics of the raw materials and/or of the manufacturing process.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Processing Statement

The film properties have been measured in a 21 µm (0.83 mil) thick cast film, extruded on a cast film line at 238 m/min (780 ft/min) line speed and temperature setting of 288 °C (550 F).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ C4LL 2818.AY Cast
C4 Linear Low Density Polyethylene

[For additional technical, sales and order assistance: Contact Us](#)

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com