

# Santoprene™ 121-70B260

## Thermoplastic Vulcanizate

### Product Description

A medium hard black thermoplastic vulcanizate (TPV) combining a low coefficient of friction with a good bonding to TPV and EPDM rubber. This grade offers excellent processability due to high shear thinning behavior for injection molding of complex geometries and excellent surface aesthetics providing color harmony with extruded profiles, without surface bleeding nor change of friction after heat aging. Santoprene 121-70B260 TPV has been designed for complex corner molding and end caps of automotive dense extruded weatherseals, either in TPV or in EPDM rubber.

### Key Features

- Specially formulated to replace thermoset EPDM rubber in automotive GRC corner molding applications
- Designed for shorter processing cycle time compared to thermoset EPDM rubber
- Adheres to vulcanized EPDM rubber and TPV
- Built-in low COF properties
- Good flowability with excellent surface aspect

### General

Availability <sup>1</sup>	<ul style="list-style-type: none"> <li>▪ Africa &amp; Middle East</li> <li>▪ Asia Pacific</li> </ul>	<ul style="list-style-type: none"> <li>▪ Europe</li> <li>▪ Latin America</li> </ul>	<ul style="list-style-type: none"> <li>▪ North America</li> </ul>
Applications	<ul style="list-style-type: none"> <li>▪ Automotive - Corner Molding and End Caps</li> </ul>	<ul style="list-style-type: none"> <li>▪ Automotive - Weather Seals</li> </ul>	
Uses	<ul style="list-style-type: none"> <li>▪ Outdoor Applications</li> </ul>		
RoHS Compliance	<ul style="list-style-type: none"> <li>▪ RoHS Compliant</li> </ul>		
Color	<ul style="list-style-type: none"> <li>▪ Black</li> </ul>		
Form(s)	<ul style="list-style-type: none"> <li>▪ Pellets</li> </ul>		
Processing Method	<ul style="list-style-type: none"> <li>▪ Injection Molding</li> </ul>	<ul style="list-style-type: none"> <li>▪ Multi Injection Molding</li> </ul>	
Revision Date	<ul style="list-style-type: none"> <li>▪ 10/25/2017</li> </ul>		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.910 g/cm <sup>3</sup>	0.910 g/cm <sup>3</sup>	ISO 1183

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Shore Hardness Shore A, 15 sec, 73°F (23°C)	68	68	ISO 868

Elastomers	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100% - Across Flow (73°F (23°C))	377 psi	2.60 MPa	ASTM D412
Tensile Stress at 100% - Across Flow (73°F (23°C))	377 psi	2.60 MPa	ISO 37
Tensile Strength at Break - Across Flow (73°F (23°C))	928 psi	6.40 MPa	ASTM D412
Tensile Stress at Break - Across Flow (73°F (23°C))	928 psi	6.40 MPa	ISO 37
Elongation at Break - Across Flow (73°F (23°C))	520 %	520 %	ASTM D412
Tensile Strain at Break - Across Flow (73°F (23°C))	520 %	520 %	ISO 37
Compression Set 158°F (70°C), 22 hr, Type 1	49 %	49 %	ASTM D395B
Compression Set 158°F (70°C), 22 hr, Type A	49 %	49 %	ISO 815

### Injection Notes

Santoprene™ TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Injection Molding Guide.

## Santoprene™ 121-70B260

Thermoplastic Vulcanizate

### Additional Information

Where applicable, test results based on fan gated, 2.0 mm injection molded plaques. Tensile strength, elongation and tensile stress are measured across the flow direction. Test results are generated by ExxonMobil test methods that may not fully conform to the ASTM and/or ISO methods. Test methods are available upon request. Compression set at 25% deflection. All products purchased directly from an ExxonMobil affiliate in Europe are REACH compliant. For products not imported into Europe by ExxonMobil, customers should assess their legal responsibilities under REACH.

### Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

For detailed Product Stewardship information, please contact Customer Service.

### Processing Statement

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Santoprene TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC. For more information, please consult our Safety Data Sheet, Injection Molding Guide and Technical Literature (TL) on "Injection Molding of Corners and End Caps to EPDM Weatherseals".

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)