

# Exxso<sup>l</sup>™ D60

## Dearomatized Fluid

Product Description	Key Features
Low odor dearomatized hydrocarbon fluid suitable for: Aerosols Blanket wash Cleaning Coatings Consumer products Metalworking Mold release agent	<ol style="list-style-type: none"> <li>1. Low aromatic content</li> <li>2. Low odor and low vapor exposure risk</li> <li>3. Narrow boiling range for optimal combination of flash point and drying time</li> <li>4. Excellent quality consistency for dependable, reliable product quality</li> </ol>

General	
Availability <sup>1</sup>	▪ Asia Pacific
Revision Date	▪ 09/01/2018

Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Aniline Point	71 °C	71 °C	ASTM D611
Aromatic Content	0.001 wt%	0.001 wt%	AMS 140.31
Color, Saybolt	+30	+30	ASTM D156
Density (15°C)	0.788 kg/dm <sup>3</sup>	0.788 kg/dm <sup>3</sup>	ASTM D4052
Evaporation Rate (n-BuAc = 100)	4.5	4.5	Calculated
Flash Point	64 °C	64 °C	ASTM D93
Kinematic Viscosity			ASTM D445
25°C	1.59 mm <sup>2</sup> /s	1.59 mm <sup>2</sup> /s	
40°C	1.28 mm <sup>2</sup> /s	1.28 mm <sup>2</sup> /s	
Refractive Index (20°C)	1.434	1.434	ASTM D1218
Vapor Pressure (20°C)	0.05 kPa	0.05 kPa	Calculated

Distillation	Typical Value (English)	Typical Value (SI)	Test Based On
Distillation Range			ASTM D86
Initial Boiling Point (IBP)	184 °C	184 °C	
Dry Point (DP)	216 °C	216 °C	

Notes
Typical properties: these are not to be construed as specifications.
<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: [www.exxonmobilchemical.com/ContactUs](http://www.exxonmobilchemical.com/ContactUs)

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.