

Exxtra™ Soft EMA2022 Cast Ethylene Methyl Acrylate Copolymer

Product Description

Exxtra™ Soft EMA2022 is an ethylene methyl acrylate copolymer specifically formulated to offer extrusion and property performance for blown and cast film applications. It produces a soft, elastic film. Exxtra™ Soft EMA2022 can produce film under 1.0 mil thickness.

General

Availability ¹	Latin America	North America	
Additive	Antiblock: No	Slip: No	Thermal Stabilizer: Yes
Applications	Disposable Gloves	Hospital Drapes	Upholstery Film
Revision Date	01/22/2019		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.943 g/cm ³	0.943 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	2.0 g/10 min	2.0 g/10 min	ASTM D1238
Methyl Acrylate Content	21.5 wt%	21.5 wt%	ExxonMobil Method
Peak Melting Temperature	176 °F	80 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	124 °F	51 °C	ASTM D1525

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	3900 psi	27 MPa	ASTM D882
Tensile Strength at Break TD	2500 psi	17 MPa	ASTM D882
Elongation at Break MD	260 %	260 %	ASTM D882
Elongation at Break TD	780 %	780 %	ASTM D882
Secant Modulus MD	8000 psi	55 MPa	ASTM D882
Secant Modulus TD	6600 psi	45 MPa	ASTM D882
Dart Drop Impact	180 g	180 g	ASTM D1709A
Elmendorf Tear Strength MD	30 g	30 g	ASTM D1922
Elmendorf Tear Strength TD	410 g	410 g	ASTM D1922

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	32	32	ASTM D2457
Haze	19 %	19 %	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Film (2 mil / 50.8 micron) made on a 3.5 inch cast film line with a 5 inch melt curtain, 80°F (27°C) chill roll temperature at a 250 ft/min take-off speed and melt temperature of 390-450°F (199-232°C).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Exxtra™ Soft EMA2022 Cast
Ethylene Methyl Acrylate Copolymer

For additional technical, sales and order assistance: [Contact Us](#)

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com