

Enable™ 4009MC Wire & Cable

Performance Polymer

Product Description

Enable™ 4009MC performance polymer resin is an ethylene 1-hexene copolymer. It can be employed in medium and high density jacketing balancing good processability with mechanical strength, abrasion and environmental stress crack resistance (ESCR). Sufficient carbon black or UV stabilizer should be added to meet cable jacketing specifications.

General

Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe North America
Additive	<ul style="list-style-type: none"> Thermal Stabilizer: Yes 	
Applications	<ul style="list-style-type: none"> Communication Cable High Voltage Jacketing 	<ul style="list-style-type: none"> Low Voltage Jacketing Medium Voltage Jacketing
Form(s)	<ul style="list-style-type: none"> Pellets 	
Revision Date	<ul style="list-style-type: none"> 06/03/2020 	

Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.938 g/cm ³	0.938 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	0.90 g/10 min	0.90 g/10 min	ASTM D1238
Peak Melting Temperature	257 °F	125 °C	ExxonMobil Method

Thermal

	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	248 °F	120 °C	ExxonMobil Method

Molded Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 2.0 in/min (50 mm/min)	3000 psi	21 MPa	ExxonMobil Method
Tensile Strength at Break 2.0 in/min (50 mm/min)	5500 psi	38 MPa	ExxonMobil Method
Elongation at Yield (2.0 in/min (51 mm/min))	10 %	10 %	ExxonMobil Method
Elongation at Break ² (2.0 in/min (50 mm/min))	840 %	840 %	ExxonMobil Method
Flexural Modulus - 1% Secant Procedure A, 0.051 in/min (1.3 mm/min)	93000 psi	640 MPa	ExxonMobil Method
Environmental Stress-Crack Resistance Condition B, 10% Igepal, F50	> 1000 hr	> 1000 hr	ExxonMobil Method
Durometer Hardness (Shore D, 15 sec)	56	56	ExxonMobil Method

Electrical

	Typical Value (English)	Typical Value (SI)	Test Based On
Volume Resistivity (500 V)	7.0E+14 ohms-m	7.0E+14 ohms-m	IEC 62631-3-1
Relative Permittivity (1 MHz)	2.31	2.31	IEC 62631-2-1
Dissipation Factor (1 MHz)	1.3E-4	1.3E-4	IEC 62631-2-1

Legal Statement

Tris(nonylphenol)phosphite (TNPP) CAS# 26523-78-4 is not intentionally used by ExxonMobil in this product. Although this product is not routinely tested for its presence, based on product composition knowledge this substance is not expected to be present. However, the fact that this substance is not intentionally used by ExxonMobil in this product does not exclude that trace levels of this substance may be present as a result of the specific characteristics of the raw materials and/or of the manufacturing process.

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Enable™ 4009MC Wire & Cable

Performance Polymer

Processing Statement

All physical properties were measured on compression molded specimens.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

² Some specimens did not break at the maximum possible elongation during testing. The data recorded for maximum tensile and elongation have been included in the calculation.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com