

# ExxonMobil<sup>TM</sup> LD 2119.LN Molding (Legacy name: ExxonMobil<sup>TM</sup> LDPE LD 521.LN Molding)

Low Density Polyethylene

#### **Product Description**

ExxonMobil™ LD 2119.LN is a low density polyethylene resin that is suitable for use in molding, extrusion, compounding and foam applications.

General					
Availability <sup>1</sup>	<ul> <li>Latin America</li> </ul>		<ul> <li>North America</li> </ul>		
Additive	<ul> <li>Antiblock: No</li> </ul>	<ul> <li>Slip: No</li> </ul>		<ul> <li>Thermal Stabilizer: No</li> </ul>	
Applications	<ul> <li>Foams</li> </ul>		<ul> <li>Injection Molding</li> </ul>		
Form(s)	<ul> <li>Pellets</li> </ul>				
Revision Date	• 06/17/2020				
Resin Properties	Typical Value	(English)	Typical Value	(SI)	Test Based On
Density	0.919	g/cm³		g/cm³	ASTM D1505
Melt Index (190°C/2.16 kg)	2.1	g/10 min	2.1	g/10 min	ASTM D1238
Peak Melting Temperature	228	°F	109	°C	ExxonMobil Method
Thermal	Typical Value	(English)	Typical Value	(SI)	Test Based On
Vicat Softening Temperature	187	°F	86.0	°C	ExxonMobil Method
Molded Properties	Typical Value	(English)	Typical Value	(SI)	Test Based On
Tensile Strength at Yield	1700	psi	11	MPa	ExxonMobil Method
Tensile Strength at Break	1500	psi	10	MPa	ExxonMobil Method
Elongation at Yield	20	%	20	%	ExxonMobil Method
Elongation at Break	445	%	445	%	ExxonMobil Method
Flexural Modulus - 1% Secant	30000	psi	210	MPa	ExxonMobil Method
Durometer Hardness					ExxonMobil
Shore A, 15 sec	95		95		Method
Shore D, 15 sec	45		45		
Impact	Typical Value	(English)	Typical Value	(SI)	Test Based On
Instrumented Dart Impact					ExxonMobil
-40°F (-40°C)		ft·lb	22		Method
73°F (23°C)	11	ft⋅lb	15	J	

# Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

## **Processing Statement**

All physical properties were measured on compression molded specimens.

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Effective Date: 06/17/2020 ExxonMobil Page: 1 of 2



ExxonMobil™ LD 2119.LN Molding Low Density Polyethylene

### For additional technical, sales and order assistance: Contact Us

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com