

PRELIMINARY DATA SHEET

Exxtra™ Performance Polyolefin BMU143N

Polypropylene, Compounded (TPO)

Product Description

A specialty thermoplastic polyolefin resin characterized by a good stiffness/toughness balance and designed for automotive interior application in which good surface finish, high scratch resistance, non-tacky and good UV resistance are required.

General

| | | |
|---------------------------|-------------------------------|-----------------------------|
| Availability ¹ | ▪ Africa & Middle East | ▪ Europe |
| Features | ▪ | ▪ High Impact Resistance |
| | ▪ Good Surface Finish | ▪ High Scratch Resistance |
| Applications | ▪ Interior General Purpose | |
| Uses | ▪ Automotive Instrument Panel | ▪ Automotive Interior Parts |
| | | ▪ Automotive Interior Trim |
| Appearance | ▪ Colors Available | |
| Form(s) | ▪ Pellets | |
| Processing Method | ▪ Injection Molding | |
| Revision Date | ▪ 07/22/2020 | |

| Physical | Typical Value (English) | Typical Value (SI) | Test Based On |
|---|---------------------------|---------------------------|---------------|
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 12 g/10 min | 12 g/10 min | ISO 1133 |
| Melt Volume-Flow Rate (MVR) | 15 cm ³ /10min | 15 cm ³ /10min | ISO 1133 |
| Density | 1.01 g/cm ³ | 1.01 g/cm ³ | ISO 1183 |

| Mechanical | Typical Value (English) | Typical Value (SI) | Test Based On |
|--|-------------------------|--------------------|---------------|
| Tensile Stress at Yield | 2970 psi | 20.5 MPa | ISO 527-2 |
| Tensile Strain at Yield | 3.6 % | 3.6 % | ISO 527-2 |
| Tensile Modulus - Secant (73°F (23°C)) | 254000 psi | 1750 MPa | ISO 527-2 |
| Flexural Modulus | 267000 psi | 1840 MPa | ISO 178 |

| Impact | Typical Value (English) | Typical Value (SI) | Test Based On |
|--------------------------------|---------------------------|-----------------------|---------------|
| Charpy Notched Impact Strength | | | ISO 179 |
| -4°F (-20°C), Complete Break | 2.6 ft-lb/in ² | 5.5 kJ/m ² | |
| 32°F (0°C), Complete Break | 4.0 ft-lb/in ² | 8.5 kJ/m ² | |
| 73°F (23°C), Partial Break | 7.6 ft-lb/in ² | 16 kJ/m ² | |

| Thermal | Typical Value (English) | Typical Value (SI) | Test Based On |
|--|-------------------------|--------------------|---------------|
| Heat Deflection Temperature (1.80 MPa) | 127 °F | 53.0 °C | ISO 75-2/A |
| Heat Deflection Temperature (0.45 MPa) | 203 °F | 95.0 °C | ISO 75-2/B |

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

This product is not intended for use in food contact application.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

PRELIMINARY DATA SHEET
Exxtral™ Performance Polyolefin BMU143N
Polypropylene, Compounded (TPO)

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

Product values shown are provisional and may change during the development process. Data contained herein was prepared pursuant to ExxonMobil's sampling and testing procedures in effect at the time the experimental product was produced.

©2020 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com