

ExxonMobil™ C6LL 18031.17

(Legacy name: ExxonMobil™ LLDPE LL 6318.17)

C6 Linear Low Density Polyethylene

Product Description

ExxonMobil™ C6LL 18031.17 resin is a narrow molecular weight hexene copolymer that offers excellent toughness, impact strength and environmental stress crack resistance. This single pellet offers a solution for applications that typically require a blend of LLDPE for easy processability and HDPE to retain desired physical properties.

General

Availability ¹	▪ Latin America	▪ North America
Additive	▪ Thermal Stabilizer: Yes	
Applications	▪ Closures ▪ Commercial articles	▪ Housewares ▪ Kitchenwares ▪ Spouts
Form(s)	▪ Pellets	
Revision Date	▪ 10/13/2022	

Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.931 g/cm ³	0.931 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	18 g/10 min	18 g/10 min	ASTM D1238

Thermal

	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	216 °F	102 °C	ASTM D1525
Peak Melting Temperature	260 °F	127 °C	ExxonMobil Method

Molded Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield	2200 psi	16 MPa	ExxonMobil Method
Elongation at Break	440 %	440 %	ASTM D638
Flexural Modulus			ASTM D790B
1% Secant	90000 psi	620 MPa	
2% Secant	77000 psi	530 MPa	
Environmental Stress-Crack Resistance			ASTM D1693B
10% Igepal, F50	750 hr	750 hr	

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Processing Statement

All physical properties were measured on compression molded specimens.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

ExxonMobil™ C6LL 18031.17
C6 Linear Low Density Polyethylene

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com