

Enable™ 4002RA

Performance Polymer

Product Description

Enable™ 4002RA is a medium density ethylene 1-hexene copolymer resin. Enable™ 4002RA performance polymer provides blown film with high stiffness and shrink along with good optical properties. Excellent bubble stability leads to high output capability in monolayer and coextruded films. Fluoropolymers, or fluorine-containing compounds, and TNPP are not intentionally added to Enable™ 4002RA.

General

Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America
Additive	<ul style="list-style-type: none"> Antiblock: No Slip: No 	<ul style="list-style-type: none"> Thermal Stabilizer: Yes Alternative Processing Aid: Yes 	
Applications	<ul style="list-style-type: none"> Collation Shrink Compression Packaging 	<ul style="list-style-type: none"> Lamination Film Multilayer Packaging Film 	
Form(s)	<ul style="list-style-type: none"> Pellets 		
Revision Date	<ul style="list-style-type: none"> 04/19/2024 		

Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.938 g/cm ³	0.938 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	0.25 g/10 min	0.25 g/10 min	ASTM D1238
Peak Melting Temperature	262 °F	128 °C	ExxonMobil Method

Film Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	2800 psi	19 MPa	ASTM D882
Tensile Strength at Yield TD	3500 psi	24 MPa	ASTM D882
Tensile Strength at Break MD	9700 psi	70 MPa	ASTM D882
Tensile Strength at Break TD	7000 psi	49 MPa	ASTM D882
Elongation at Break MD	490 %	490 %	ASTM D882
Elongation at Break TD	810 %	810 %	ASTM D882
Secant Modulus MD - 1% Secant	78000 psi	540 MPa	ASTM D882
Secant Modulus TD - 1% Secant	110000 psi	730 MPa	ASTM D882
Dart Drop Impact	60 g	60 g	ASTM D1709
Elmendorf Tear Strength MD	10 g	10 g	ASTM D1922
Elmendorf Tear Strength TD	600 g	600 g	ASTM D1922
Puncture Force	11 lbf	50 N	ExxonMobil Method
Puncture Energy	19 in-lb	2.2 J	ExxonMobil Method

Optical Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	26	26	ASTM D2457
Haze	21 %	21 %	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Fluoropolymers, or fluorine-containing compounds, and tris(nonylphenol) phosphite (TNPP) CAS# 26523-78-4 are not intentionally used by ExxonMobil in this product. Although this product is not routinely tested for their presence, based on product composition knowledge these substances are not expected to be present. However, the fact that these substances are not intentionally used by ExxonMobil in this product does not exclude that trace levels of these substances may be present as a result of the specific characteristics of the raw materials and/or of the manufacturing process.

Processing Statement

Film (1 mil/25.4 micron) made on a 2.5 inch blown film line equipped with 2.5:1 blow-up ratio, 30 mil die gap, 16 in frostline, 425°F melt temperature and 10 lbs/die in/hr.

Enable™ 4002RA Performance Polymer

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com