

Exact™ 9162

Ethylene-based Plastomer Resin

Product Description		Key Features		
<p>Exact™ 9162 is an ethylene butene copolymer produced using ExxonMobil's proprietary metallocene catalyst technology. It exhibits outstanding elastomeric properties including superior low temperature toughness. Exact™ 9162 is designed for modification of polypropylene and polyethylene in a wide range of applications such as compounding. This resin is compatible with polyolefins like polypropylene (PP), polyethylene (PE) and ethylene-vinyl acetate copolymer resin (EVA).</p>		<ul style="list-style-type: none"> PP / TPO modification. Low density. Low crystallinity. Free flowing pellets. EVA foam modification. 		
General				
Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America 	
Applications	<ul style="list-style-type: none"> Compounding and TPO General purpose elastomer 	<ul style="list-style-type: none"> Injection Molding Polymer Modification 		
Form(s)	<ul style="list-style-type: none"> Pellets 			
Revision Date	<ul style="list-style-type: none"> 04/19/2024 			
Physical				
	Typical Value (English)	Typical Value (SI)	Test Based On	
Density / Specific Gravity	0.862 g/cm ³	0.862 g/cm ³	ASTM D792	
Melt Index (190°C/2.16 kg)	1.2 g/10 min	1.2 g/10 min	ExxonMobil Method	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.4 g/10 min	2.4 g/10 min	ExxonMobil Method	
Hardness				
	Typical Value (English)	Typical Value (SI)	Test Based On	
Durometer Hardness			ASTM D2240	
Shore A	44	44		
Shore D	8	8		
Mechanical				
	Typical Value (English)	Typical Value (SI)	Test Based On	
Tensile Stress	200 psi	1.4 MPa	ExxonMobil Method	
Tensile Stress at 100% (73°F (23°C))	130 psi	0.90 MPa	ExxonMobil Method	
Elongation at Break	604 %	604 %	ExxonMobil Method	
Flexural Modulus - 1% Secant	590 psi	4.1 MPa	ASTM D790	
Elastomers				
	Typical Value (English)	Typical Value (SI)	Test Based On	
Tensile Stress at 300% (73°F (23°C))	174 psi	1.20 MPa	ExxonMobil Method	
Tear Strength (Die C)	76.8 lbf/in	13.4 kN/m	ExxonMobil Method	
Mooney Viscosity (ML 1+4, 257°F (125°C))	17 MU	17 MU	ExxonMobil Method	
Thermal				
	Typical Value (English)	Typical Value (SI)	Test Based On	
Vicat Softening Temperature	101 °F	38.3 °C	ExxonMobil Method	
Additional Information				
All physical properties were measured on compression molded specimens.				

Exact™ 9162
Ethylene-based Plastomer Resin

Legal Statement

For detailed Product Stewardship information, please contact Customer Service.

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com