

Paxon™ AU60-007

High Density Polyethylene Resin

Product Description

AU60-007 is a homopolymer HDPE film grade designed to improve stiffness and barrier in coextrusion or in PE blends. When blended with LLDPE or metallocene LLDPE, AU60-007 improves their processability.

General

Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America
Additive	<ul style="list-style-type: none"> Antiblock: No Slip: No 	<ul style="list-style-type: none"> Processing Aid: No Thermal Stabilizer: Yes 	
Applications	<ul style="list-style-type: none"> Blown Film Bread Bags Collation Shrink Food Packaging Form Fill And Seal Packaging Freezer Film 	<ul style="list-style-type: none"> General Packaging Industrial Packaging Label Film Lamination Film Multilayer Packaging Film Overwrap Film 	<ul style="list-style-type: none"> Packaging Films Shoppers Shrink Film Stand Up Pouches
Form(s)	<ul style="list-style-type: none"> Pellets 		
Revision Date	<ul style="list-style-type: none"> 05/31/2024 		

Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.963 g/cm ³	0.963 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	0.73 g/10 min	0.73 g/10 min	ASTM D1238
Peak Melting Temperature	275 °F	135 °C	ExxonMobil Method

Film Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD 20 in/min (500 mm/min)	4700 psi	32 MPa	ExxonMobil Method
Tensile Strength at Yield TD 20 in/min (500 mm/min)	4100 psi	28 MPa	ExxonMobil Method
Tensile Strength at Break MD 20 in/min (500 mm/min)	6900 psi	47 MPa	ExxonMobil Method
Tensile Strength at Break TD 20 in/min (500 mm/min)	4700 psi	33 MPa	ExxonMobil Method
Elongation at Break MD 20 in/min (500 mm/min)	420 %	420 %	ExxonMobil Method
Elongation at Break TD 20 in/min (500 mm/min)	8 %	8 %	ExxonMobil Method
Secant Modulus MD - 1% Secant	168000 psi	1160 MPa	ExxonMobil Method
Secant Modulus TD - 1% Secant	220000 psi	1510 MPa	ExxonMobil Method
Dart Drop Impact (Method A)	< 70 g	< 70 g	ExxonMobil Method
Elmendorf Tear Strength MD	7 g	7 g	ASTM D1922
Elmendorf Tear Strength TD	510 g	510 g	ASTM D1922

Optical Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	11	11	ASTM D2457
Haze	> 30 %	> 30 %	ASTM D1003

Additional Information

Monolayer Film:

AU60-007 can be added to LDPE, LLDPE or mLLDPE films to increase stiffness when high transparency is not mandatory.

Paxon™ AU60-007
High Density Polyethylene Resin

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Film (1.0 mil/25.4 micron) made from AU60-007 resin on a 2.5 inch (63.5 mm) blown film line with a 2.5:1 blow-up ratio, a melt temperature of 405-425°F (207-218°C), a 60 mil (1.5 mm) die gap at a rate of 10 lbs/hr/in die circumference (1.79 kg/hr/cm).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com