

ExxonMobil™ C6LL 0825.36

C6 Linear Low Density Polyethylene

Product Description

ExxonMobil™ C6LL 0825.36 is an ethylene 1-hexene linear low density polyethylene film resin. Films made from ExxonMobil™ C6LL 0825.36 have outstanding tensile, stiffness and toughness properties. These superior properties, along with good drawdown capability, permit usage in many demanding packaging applications.

General

Availability ¹	<ul style="list-style-type: none"> Latin America North America
Additive	<ul style="list-style-type: none"> Antiblock: 5000 ppm Slip: No Processing Aid: Yes Thermal Stabilizer: Yes
Applications	<ul style="list-style-type: none"> Freezer Film Grocery Sacks Heavy Duty Bags Merchandise Bags
Form(s)	<ul style="list-style-type: none"> Pellets
Revision Date	<ul style="list-style-type: none"> 10/15/2024

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.925 g/cm ³	0.925 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	0.80 g/10 min	0.80 g/10 min	ASTM D1238
Peak Melting Temperature	257 °F	125 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	226 °F	108 °C	ExxonMobil Method

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	1700 psi	12 MPa	ASTM D882
Tensile Strength at Yield TD	1900 psi	13 MPa	ASTM D882
Tensile Strength at Break MD	8300 psi	60 MPa	ASTM D882
Tensile Strength at Break TD	6700 psi	46 MPa	ASTM D882
Elongation at Break MD	530 %	530 %	ASTM D882
Elongation at Break TD	790 %	790 %	ASTM D882
Secant Modulus MD - 1% Secant	38000 psi	260 MPa	ASTM D882
Secant Modulus TD - 1% Secant	46000 psi	320 MPa	ASTM D882
Dart Drop Impact	130 g	130 g	ASTM D1709A
Elmendorf Tear Strength MD	220 g	220 g	ASTM D1922
Elmendorf Tear Strength TD	670 g	670 g	ASTM D1922
Puncture Force	11 lbf	47 N	ExxonMobil Method
Puncture Energy	33 in-lb	3.7 J	ExxonMobil Method

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	58	58	ASTM D2457
Haze	14 %	14 %	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Film (1.0 mil/25.4 micron) made on a 2.5 inch (63.5 mm) blown film line with a 2.5:1 blow-up ratio, a melt temperature of 395–415°F (202–213°C), a 60 mil (1.52 mm) die gap at a rate of 10 lbs/hr/in die circumference (1.79 kg/hr/cm).

ExxonMobil™ C6LL 0825.36
C6 Linear Low Density Polyethylene

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: [Contact Us](#)

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com