

# Exceed™ Flow PP3655E1

## Polypropylene Homopolymer

### Product Description

Exceed™ Flow PP3655E1 is a high MFR homopolymer resin designed for spunbond nonwovens. The resin is particularly suited for excellent spinning for finer fiber, uniform, high quality fabrics. Formulated for application requiring low color and low gas fading discoloration. Produced with a catalyst system that does not include intentionally added phthalate compounds. This product can be used for injection molding, thin wall injection molding (TWIM), compounding, and others.

### General

Availability <sup>1</sup>	<ul style="list-style-type: none"> <li>Asia Pacific</li> <li>Europe</li> </ul>
Features	<ul style="list-style-type: none"> <li>Fine Fibers</li> <li>Good Color Stability</li> <li>Good Processability</li> <li>No Intentionally Added Phthalates</li> </ul>
Uses	<ul style="list-style-type: none"> <li>Compounding</li> <li>Consumer Applications</li> <li>Fibers</li> <li>Medical/Healthcare Applications<sup>2</sup></li> <li>Personal Care</li> <li>Spunbond Nonwovens</li> <li>Thin-walled Parts</li> </ul>
Appearance	<ul style="list-style-type: none"> <li>Natural Color</li> </ul>
Form(s)	<ul style="list-style-type: none"> <li>Pellets</li> </ul>
Processing Method	<ul style="list-style-type: none"> <li>Compounding</li> <li>Fiber (Spinning) Extrusion</li> <li>Filament Extrusion</li> <li>Injection Molding</li> </ul>
Revision Date	<ul style="list-style-type: none"> <li>05/20/2025</li> </ul>

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	58 g/10 min	58 g/10 min	ASTM D1238
Density	0.900 g/cm <sup>3</sup>	0.900 g/cm <sup>3</sup>	ExxonMobil Method

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 2.0 in/min (51 mm/min)	4960 psi	34.2 MPa	ASTM D638
Elongation at Yield (2.0 in/min (51 mm/min))	9.0 %	9.0 %	ASTM D638
Flexural Modulus - 1% Secant (0.051 in/min (1.3 mm/min))	214000 psi	1480 MPa	ASTM D790A

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact (73°F (23°C))	0.39 ft·lb/in	21 J/m	ASTM D256A
Gardner Impact (73°F (23°C))	43.1 in·lb	4.87 J	ASTM D5420

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Deflection Temperature Under Load (DTUL) at 264psi - Unannealed	127 °F	53.0 °C	ExxonMobil Method
Vicat Softening Temperature	306 °F	152 °C	ExxonMobil Method

Optical	Typical Value (English)	Typical Value (SI)	Test Based On
Haze	56.0 %	56.0 %	ASTM D1003

### Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Exceed™ Flow PP3655E1  
Polypropylene Homopolymer

#### Notes

Typical properties: these are not to be construed as specifications.

Reported data was generated using injection molded samples.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

<sup>2</sup> This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

For additional technical, sales and order assistance: [Contact Us](#)

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

[exxonmobilchemical.com](http://exxonmobilchemical.com)